

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup>:</b> <b>A62D 1/00</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 98/03228</b> <b>(43) International Publication Date:</b> 29 January 1998 (29.01.98)
<b>(21) International Application Number:</b> PCT/GR97/00028 <b>(22) International Filing Date:</b> 15 July 1997 (15.07.97)  <b>(30) Priority Data:</b> 960100257      22 July 1996 (22.07.96)      GR  <b>(71)(72) Applicant and Inventor:</b> VALKANAS, George, N. [GR/GR]; 14 Constantinoupoleos Street, GR-151 32 Maroussi (GR).  <b>(74) Agent:</b> KILIMIRIS, Tassos, Anastase; 7 Hatziyianni Mexi Street, GR-115 28 Athens (GR).		<b>(81) Designated States:</b> AU, BG, BR, CA, CN, CZ, HU, KR, MX, NO, NZ, PL, RO, SG, TR, UA, US, YU, Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> METHOD AND PRODUCTS TO FACE FIRES  <b>(57) Abstract</b>  Method for extinguishing fires by applying to the boundaries of the fire an aqueous suspension comprising 1 to 3 % by weight of a polymeric product, which contains up to 400 g of endomolecularly bound water per gram of polymer, and optionally other complementary agents, such as detergents, emulsifiers, adhesion promoters and inorganic compounds (e.g. carbonates, sulfates, silicates, etc.).		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakistan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

### METHOD AND PRODUCTS TO FACE FIRES

The most extended disasters nowadays which destroy Earth's civilisation and terrorises life is that of fires occurring every summer, every year, by which more and more green is destroyed and life is damaged and with those events are vanished fundamental elements of life. The destruction of forests and elements of life with fires results to damaged ecosystems.

10

Extended fires are also the result of another destructive event, that of abandoning the mountainous areas, the population thus moving for living in plains and in large cities, which is connected with increase in water consumption. These changes of habitat have resulted to abandoning of the vast mountainous areas which largely control the water balance and the biological action on Earth.

20 There is a need to enter fire facing for survival and to enter fighting the catastrophic fires in which the man is rather weak and in spite of the fact that all available means for quenching water such as aeroplanes, helicopters, ships, tankers are employed. The means in use for fire fighting are water and carbon dioxide applied by all transport means mentioned which are continuously improved but are not that successful to face the increase in fire damages.

30 In the meantime it has been scientifically proved that adding little water on the fire edges is a successful

fire facing approach. Based on that a new scientific relief has been developed, that could lead successfully facing the Earth's catastrophe.

- 5 We have extensively studied the problem of fire facing and have thought and worked to advance products and techniques which lead to successful fire fighting. The original highly profitable approach has derived from our conviction that need and could be discovered solutions
- 10 with adding to fire edges products can release much water by which the fire ceases at once. And in case these products are organic and could be destroyed by burning their remains could secure effective fire fighting in the area is involved.

15

- We have worked most extensively to fulfil the above and by R & D work we have developed original and most profitable products for that action and we have also advanced proper techniques leading to successful fire
- 20 facing. The products we have developed are derived from market polymers or from recycled polymers which by processing in different stages become macroplegmatic and of stability to introduce in them polar grouping at high density with which they acquire capacity to absorb water
- 25 up to 300 times their weight which water is kept endomolecularly and the water is held thus very strongly.

- These products, tried in practice, are easily suspended in water in pure form or with selective additives
- 30 according to needs. The additives which can be added as improvements are : detergents, emulsifiers, adhesives and

materials that do not burn such as carbonates, sulphates, silicates etc. so that the coverage of use can be highly expanded.

- 5 The polymeric macroplegmatic products that absorb water up to 300 times endomolecularly, are directed to the fire edges where they are burned releasing much water to fight fires at once. That result has been proved in practice with very successful results in speed of action , in  
10 difficult fire control and in wide coverage. Some such results of application are described in the following.

a. Water to face fire contains 2% polymeric material, 1% calcium carbonate pulverised and 0.5% detergent. This  
-15 was used to face fires developed in wood. A very rapid control of fire was observed and also that fire could not develop for 120 minutes.

b. Water to face fire containing 1% polymeric material 1% pulverised calcium carbonate was used to face fires  
20 developed in a forest. The fire was controlled in very short time and the area where water was thrown did not show firing ability.

c. Water contained in emulsion 2% polymeric material, 0.1% detergent and 1% starch to ensure emulsion  
25 stability This was used to face fires developed in car tyres. The control of fire was rapid and there was no possibility of a new fire developing in those tyres.

d. After these successful trials was demonstrated fire facing from aeroplane. The water contained 1% polymeric  
30 material by weight, and thrown on the fire followed by very impressive result that the fire was controlled

quickly in a wide area and the forest with the solution overthrown did not show efficiency to develop fire.

The originality and the importance of our invention which  
5 deals with a problem of survival in our planet is evident. It is showing high potential in dealing with fires. It constitutes a first such possibility to face efficiently the fires in city life out of cities, in forests, in cultivating areas and everywhere.

10

We know the magnitude of utility of what we are proposing and also the magnitude of our responsibility on that solution. We hope that our lives can change with the possibility developed to face fires and the conception of  
15 life and the security to offer is a relief to the overpopulated world.

But the fires have many faces in developing and in destroying and it is necessary that we all collaborate to  
20 create a complete solution in the facing of fires so that security can be achieved.

## EXAMPLE 1

25 Polystyrene recycled 100 kg is diluted in 300 litres of 1,2-dichloroethylene solvent and in that solution is added 1 kg of dibenzyl-X-dichloro-dibenzyl chloride as crosslinking agent. The resulting solution is heated to 40° C and then is added 40 ml of concentrated sulfuric  
30 acid. After 5 minutes of agitation crosslinking has occurred and when the mixture could not be agitated the

product is taken out, is minced in a machine and then is suspended into 300 litres of solvent. In the suspension resulted at 68° C is added chlorosulfonic acid 2,2 M/M to benzene rings and sulfonation begins. The sulfonation  
5 reaction is followed with estimating the hydrogen chloride liberation. Then two layers are gradually formed: that of polymeric insoluble mass and that of solvent and those layers are separated by centrifuging in a decanter The polymeric mass is neutralised with  
10 concentrated sodium hydroxide solution and then is directed in sodium chloride 20% solution where most of the water is expelled from the polymeric mass and the remaining water is taken out by taking the mass under electric voltage of 20 V from where the polymeric mass is  
15 received practically free of water. The polymeric mass at the end is taken into a reactor where is heated under vacuum to 160° C where the mass becomes soft and homogenic. Finally it is taken into desalinated water and after 6 hr. into it then the polymeric mass had water  
20 absorption capacity of 225 (times its weight) and an ion-exchange strength of 4,94.

## EXAMPLE 2

25 Polystyrene 100 kg is dissolved into 300 litres of solvent where acetic acid is added to resist sulfone groups formation in quantity 15% to the solvent volume. It is subjected to sulfonation by adding chlorosulfonic acid 2,2 M/M of benzene rings as a 20% solution in the  
30 solvent at 68° C. Two layers are gradually formed. These are separated by decanting and the polymeric product is

further treated like in Example 1. Finally a product of water absorption capacity 350 and ionic exchange strength of 4,96 is obtained.

5

## EXAMPLE 3

A copolymer of acrylonitrile and styrene 40:60 in 10 kg. quantity is diluted into 30 litres of solvent containing 18% acetic acid and in that is added chlorosulfonic acid  
10 2,2 M/M of benzene rings. After the sulfonation treatment a glassy insoluble product separated by decanting is received. It is treated like in example 1 and finally a product with two ionic grouping one acetic and one sulfonic is received. The product finally had a water  
15 absorption capacity of 270.

## EXAMPLE 4

Fully hydrogenated SBR in quantity of 10 kg is diluted  
20 into 30 litres of solvent and cross-linked with the agent dibenzyl-X-dimethylbenzyl-chloride using sulfuric acid as catalyst according to the example 1. The thick mass resulting after 20 minutes agitation was minced and subjected into 30 litres of solvent. Then it was  
25 sulfonated with oleum (60% SO<sub>3</sub>) in quantity 3 M/M benzene rings at 100 with cooling. The final product after purification according to the above had a water absorption capacity of 103 and an ion-exchange strength 4,1.



## EXAMPLE 5

## Preparation of fire facing product formulations

## 5 Product A

To be used with water quenching in expanded areas

It is used product of Examples 1 to 4 in pure form and is  
taken into water for equilibration. Product of the  
10 resulted quality is suspended into quenching water in  
quantity 1-3% and is used to control fires by directing  
those products into the fire edges.

## Product B

15

Product to be used for personal utilisation to face small  
fires. It is suggested to use the products in emulsions  
rather like in the following formulation.

20 Polymeric product 2-3% Detergent 0.1 %

Starch or petroleum distillates 0.5%

And for better pumping because of higher viscosity are  
added also inorganic pulverised products such as kalk,  
sulfates, sand, silicates.

25

## Product C

To face fires developed in organic volatile solvents that  
burn easily the action should be concentrated and rapid.

30 The polymeric products of 1-4 examples are utilised in

higher concentrations up to 10% if that is possible and are pumped.

Remark. The polymeric products contain much water thus  
5 their pumping should not involve high pressure. It is much better to use running water or by applying water pressure or vacuum.

## CLAIMS

1. Method of quenching fires with the use of special products, multiprocessed polymers acquiring  
5 macroplegmatic structures permitting the introduction of ionic grouping at high density which then absorb high water quantities up to 400 gr. water/gr. of polymer intermolecularly, which products added to fire edges by burning or by decomposing liberate much water with which  
10 the fire edges are quenched and the area becomes unburnable.
2. Method according to claim 1 by which the special products which advance complete fire quenching in forests, in cultivated areas, in cities, in industrial  
15 units, in transport vehicles when added to the fire edges result to quenching of fires and with the water containing the products is advanced in the area creating fire safe conditions.
3. Method according to the claims 1 & 2 by which the  
20 quenching fire products are advanced by all available means and techniques, with aeroplanes, with helicopters, with tankers, which pump water to quench fires where the special products are used in quantities 1-3% by weight.
4. Method according to claims 1 & 3 by which the fire  
25 quenching products are burned or decomposed in the fire edges and the excess of them turns the area to fire safe conditions.
5. Method according to claims 1 & 2 by which in the fire quenching products are added and other products  
30 facilitating the action such as detergents, emulsifiers, adhesive agents and inorganic materials such as kalk,

sulfates, silicates in pulverised form which do not burn and are mixable and are useful assisting in the fire quenching action.

6. Method of fire quenching according to the claims 1 to 5 by which are used original special fire quenching products which are multiprocessed market polymers or copolymers to acquire ability to absorb water up to 400 gr. of water/gr. of polymer, with the water being kept intermolecularly strongly requiring pressure to take it out, which being introduced on the fire edges advance rapid fire quenching by releasing much water to the fire edges independent to the expansion of fires and to the kind of fires and independent to the substratum, being advanced by all available techniques and means making in the quenching water 1-3% by weight and in solution or suspension may also be added special additives such as detergents, emulsifiers, pulverised inorganic products do not burn which all are applied with the means and the techniques used in fire quenching by aeroplanes, helicopters, tankers, and others and by which the fires are quenched rapidly and profitably.

# INTERNATIONAL SEARCH REPORT

International Application No

PC1/GR 97/00028

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 6 A62D1/00

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 A62D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,X	EP 0 774 279 A (STOCKHAUSEN INC.) 21 May 1997 see column 3, line 8 - column 4, line 5 see column 6, line 16 - column 7, line 1 see column 7, line 33 - line 57; claims	1-6
X	EP 0 649 669 A (ÖKO-TEC UMWELTSCHUTZSYSTEME) 26 April 1995 see column 3, line 36 - column 5, line 15; claims; examples 3-12,14	1-6
X	DE 37 16 304 A (H. VON BLÜCHER ET AL) 24 November 1988 see the whole document	1,2,4,5
-/-		

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*B\* document member of the same patent family

Date of the actual completion of the international search

7 October 1997

Date of mailing of the international search report

17-10-1997

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Fletcher, A

# INTERNATIONAL SEARCH REPORT

International Application No

PC/GR 97/00028

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 199 897 A (H. VON BLÜCHER ET AL) 5 November 1986 see page 4, line 10 - page 6, line 3 see page 7, line 1 - line 26 see page 8, line 21 - page 9, line 4; claims ---	1,2,4,5
X	DATABASE WPI Section Ch, Week 9206 Derwent Publications Ltd., London, GB; Class A97, AN 92-046363 XP002042788 & JP 03 292 969 A (OSAKA YUKI KAGAKU KOGYO) , 24 December 1991 see abstract ---	1,2,4,5
X	DATABASE WPI Section Ch, Week 8125 Derwent Publications Ltd., London, GB; Class A97, AN 81-45053d XP002042789 & JP 56 049 167 A (MIYATA KOGYO) , 2 May 1981 see abstract ---	1,2,4,5
Y	FR 2 615 399 A (LAFARGE NOUVEAUX MATERIAUX) 25 November 1988 see page 1, line 32 - page 2, line 22 see page 3, line 1 - line 35 see page 5, line 1 - line 31 see page 7, line 17 - line 23 ---	1-6
Y	DATABASE WPI Section Ch, Week 9024 Derwent Publications Ltd., London, GB; Class A12, AN 90-182640 XP002042790 & JP 02 120 339 A (HAKUDA KAGAKU KAIHA) , 8 May 1990 see abstract -----	1-6

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GR 97/00028

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0774279 A	21-05-97	AU 4796396 A CA 2176076 A	22-05-97 15-05-97
EP 0649669 A	26-04-95	DE 4336319 A AU 7744694 A CA 2134130 A JP 7255870 A	27-04-95 11-05-95 26-04-95 09-10-95
DE 3716304 A	24-11-88	AU 602766 B AU 1533388 A CA 1307393 A CN 1015511 B DE 3873430 A DK 266188 A EP 0295412 A JP 63309279 A KR 9608612 B NO 175520 B US 4978460 A	25-10-90 17-11-88 15-09-92 19-02-92 10-09-92 16-11-88 21-12-88 16-12-88 28-06-96 18-07-94 18-12-90
EP 0199897 A	05-11-86	DE 3515865 A AU 595198 B AU 5706686 A CA 1276442 A DK 203786 A FI 98271 B JP 8008937 B JP 62084779 A US 4978460 A US 5190110 A	06-11-86 29-03-90 06-11-86 20-11-90 04-11-86 14-02-97 31-01-96 18-04-87 18-12-90 02-03-93
FR 2615399 A	25-11-88	NONE	